Amendments to the Claims:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A synthetic resin container possessing a higher gas barrier property, and having a coating film possessing a higher gas barrier property and positioned on an inner surface and/or outer surface of a body of the container, characterized in wherein:

that said coating film comprises a layered coating including at least a gas barrier coating and a cover coating, said cover coating being positioned at a topmost side of said coating film; film,

that-said cover coating includes a layer positioned at a topmost side of said cover coating and possessing such a water repellency that said layer has a contact angle with water of 80° to 100°, 100°; and

that the layers constituting said coatings, respectively, are each formed by vapor deposition and each have a refractive index in a range of 1.3 to 1.6.

- 2. (Original) The synthetic resin container of claim 1, wherein said gas barrier coating and said cover coating are arranged adjoinedly to each other.
- 3. (Previously Presented) The synthetic resin container of claim 1, further comprising a base coating between said layered coating and a topmost surface of said container body.
- 4. (Previously Presented) The synthetic resin container of claim 1, wherein said gas barrier coating is a silicon oxide compound layer including silicon oxide as a main component, and said cover coating is an organic silicon compound layer.

- 5. (Original) The synthetic resin container of claim 4, further comprising a base coating between said layered coating and a topmost surface of said container body, and wherein said base coating comprises an organic silicon compound layer.
- 6. (Previously Presented) The synthetic resin container of claim 2, further comprising a base coating between said layered coating and a topmost surface of said container body.
- 7. (Previously Presented) The synthetic resin container of claim 2, wherein said gas barrier coating is a silicon oxide compound layer including silicon oxide as a main component, and said cover coating is an organic silicon compound layer.
- 8. (Previously Presented) The synthetic resin container of claim 7, further comprising a base coating between said layered coating and a topmost surface of said container body, and wherein said base coating comprises an organic silicon compound layer.